

鍍錫硬銅絞線 鍍錫軟銅絞線

STRANDED TINNED HARD-DRAWN AND SOFT COPPER CONDUCTORS

CNS 1367、672；JCS 230A、229A

公稱 截面積 Nominal Area	導體構造 Conductor Construction	參考值 Reference			最大導體電阻 Resistance 20°C Max.		拉斷力 Breaking Load	標準長度 Length of each Coil or Reel
		截面積 Area	絞合外徑 Overall Dia.	重量 Weight	軟 Soft	硬 Hard	硬(最小) Hard (Min.)	
mm ²	No./mm	mm ²	mm	kg/km	Ω/km	Ω/km	kg	m
1000	127/3.2	1,021	41.6	9,315	0.0180	0.0179	33,090	300
850	127/2.9	838.8	37.7	7,651	0.0220	0.0217	27,180	300
725	91/3.2	731.8	35.2	6,655	0.0251	0.0248	23,710	300
600	91/2.9	601.1	31.9	5,466	0.0306	0.0303	19,480	300
500	61/3.2	490.6	28.8	4,448	0.0373	0.0370	15,890	300
400	61/2.9	402.9	26.1	3,654	0.0455	0.0450	13,060	300
325	61/2.6	323.8	23.4	2,937	0.0566	0.0560	10,490	300
250	61/2.3	253.5	20.7	2,298	0.0723	0.0715	8,120	300
200	37/2.6	196.4	18.2	1,766	0.0930	0.0920	6,360	500
150	37/2.3	153.7	16.1	1,390	0.119	0.118	4,980	600
125	19/2.9	125.5	14.5	1,129	0.145	0.143	4,070	600
100	19/2.6	100.9	13.0	907.6	0.180	0.178	3,270	600
80	19/2.3	78.95	11.5	710.3	0.230	0.228	2,560	1,000
60	19/2.0	59.70	10.0	537.0	0.304	0.301	1,930	1,000
50	19/1.8	48.36	9.0	435.1	0.380	0.376	1,610	1,000
38	7/2.6	37.16	7.8	334.4	0.489	0.484	1,200	300
30	7/2.3	29.09	6.9	261.7	0.625	0.618	942	300
22	7/2.0	21.99	6.0	197.9	0.826	0.818	713	300
14	7/1.6	14.08	4.8	126.7	1.30	1.29	469	500
8.0	7/1.2	7.917	3.6	71.19	2.32	2.30	264	500
5.5	7/1.0	5.498	3.0	49.46	3.34	3.31	183	500
3.5	7/0.8	3.519	2.4	31.66	5.28	5.22	117	500
2.0	7/0.6	1.979	1.8	17.80	—	9.28	—	500
1.4	7/0.5	1.375	1.5	12.37	—	13.4	—	500
1.25	7/0.45	1.113	1.35	10.02	—	16.7	—	500
0.9	7/0.4	0.8799	1.2	7.913	—	20.4	—	500